

# PVC PRESSURE PIPE SCHEDULE 80 SOLVENT WELD

CNWPVC-80SW JANUARY, 2013

PLEASE ORDER BY PART NUMBER.

				MIN.	WEIGHT PER	MIN. BELL	FEET PER	PERCENT OF	PART
SCH 80	SIZE	O.D.	I.D.	WALL	100'	LENGTH	PALLET	TL	NO.
PRESSURE PIPE	6"	6.625	5.761	.432	546.56	6.000	400	5.6	43160
PVC1120	8	8.625	7.625	.500	830.24	7.000	280	6.3	43168
ASTM D-1785	10	10.750	9.564	.593	1230.78	7.500	160	6.2	43171
	12	12.750	11.376	.687	1692.06	8.000	120	6.7	43176

SCH-80 PIPE IS RECOMMENDED FOR THREADING.

SCH-80 PIPE IS FURNISHED IN BELLED END 20' LENGTHS AND IS GRAY COLOR.



### PRESSURE RATINGS FOR CRESLINE - PVC PIPES AT 73.4° F

SIZE	6	8	10	12
SCH-80	280	250	230	230

## CONVERSION CHART FOR PRESSURE RATINGS AT VARIOUS TEMPERATURES FOR CRESLINE - PVC PIPES

TEMPERATURE °F	73.4°	80°	90°	100°	110°	120°	130°	140°
CONVERSION FACTOR	1.00	.88	.75	.62	.50	.40	.30	.22

PRESSURE RATING IS THE ESTIMATED MAXIMUM PRESSURE THAT WATER AS THE MEDIUM IN THE PIPE CAN EXERT CONTINOUSLY FOR A LONG TIME WITH A HIGH DEGREE OF CERTAINTY THAT FAILURE OF THE PIPE WILL NOT OCCUR.

### DO NOT USE PLASTIC PIPE AND FITTINGS FOR COMPRESSED AIR.

#### PALLET QUANTITIES PVC PRESSURE PIPE

PIPE	FEET PER	WT. PER PALLET		
SIZE	PALLET	SCH-80		
6	400	2186		
8	280	2325		
10	160	1969		
12	120	2030		