

Bulletin No. T-1

February, 2024

**PRESSURES AND TEMPERATURES:** In selecting any type of plastic pipe for any installation, consideration must be given to pressure ratings and temperatures. Pressure ratings go **down** as temperatures go up. Exposure to weather temperature variations, heat of sun, or other heat factors should always be taken into account. All Cresline Specification Sheets include "Pressure Rating" tables for the respective pipes.

**CHEMICAL RESISTANCE:** All types of Cresline plastic pipe are highly resistant to a wide variety of corrosive chemicals. As a guide for the type of Cresline pipe best suited to resist corrosion of a specific chemical, please refer to the Chemical Resistance Chart, Bulletin No. T-4. When consulting the Chart, please bear in mind that plastic pipe is not a "cure all" and, in some cases, may only provide longer life.

**OILS AND SOAPS:** Cresline PVC pipe is the type best suited for handling most of these materials. Cresline polyethylene pipe is not recommended for the transmission of these materials.

**PLASTIC THREADED CONNECTIONS:** When threading plastic to plastic or plastic to steel, precaution should be taken to prevent excessive tightening, causing damage to the plastic fitting. **The correct degree of tightness may be determined by threading the connection two turns past finger tight.** Do not use Pipe dope. However, the use of Teflon tape is recommended.

**BENDING:** In bending Cresline PVC, excellent results can be obtained by heating the pipe in a fluid bath or hot air oven at 225° F. for five minutes and bending it around a form of corresponding radius. To prevent flattening, the pipe can be filled with sand or bent around a pipe bending form grooved to the depth and the same radius as the outside diameter of the pipe. Due to a certain amount of recovery, the pipe should be bent beyond design to allow for this spring-back. After bending, the pipe should be cooled with water while still on the form. Do not use PVC pipe that has been bent in a pressure system.

**NOTE: DO NOT USE PLASTIC PIPE AND FITTINGS FOR COMPRESSED AIR SYSTEMS.**

**(OVER)**

**EXPANSION AND CONTRACTION:** Highly important is the variation in length of plastics when temperature is changing. This fact should always be taken into account when installing pipe lines. The following figures may be used as a guide to determine expansion and contraction:

PVC-----4" per 1000' per 10° F temperature change

HD & SP (Polyethylene)-----11" per 1000' per 10° F temperature change

HC (CPVC)-----4" per 1000' per 10° F temperature change

(Above applies to all pipe sizes)

**SUPPORTS:** Special care must be exercised in the spacing of supports on horizontal runs of plastic pipe. Supports should have a reasonably broad contact surface. Wires and rods are not recommended if in direct contact with the pipe.

The following table is based on PVC SCH 40 pipe filled with water (from ASTM F645).

PIPE SIZE	SPACING ---- FT.		
	AT 73° F	AT 100° F	AT 140° F
1/2"	4	3 3/4	3 1/2
3/4"	4 1/4	4 1/4	4
1"	4 3/4	4 1/2	4 1/4
1 1/4"	5 1/4	5	4 3/4
1 1/2"	5 1/2	5 1/4	5
2"	6	5 1/4	5 1/2
2 1/2"	7	6	6
3"	7 1/4	7	6 1/2
4"	8	7 3/4	7 1/4
6"	9 1/4	9	8 1/2
8"	10 1/4	10	9 1/2
10"	11 1/4	10 3/4	10 1/4
12"	12	11 3/4	11

For Cresline polyethylene pipe, use twice the number of supports.

For fluids twice the specific gravity, use twice the number of supports suggested above.

For Schedule 80 pipe, spacing may be increased 20%.

For SDR 26, SDR 21, decrease spacing 25% - 50%.

**CRESLINE PLASTIC PIPE CO., INC.**

600 Cross Pointe Blvd.  
264 Silver Spring Rd.  
2100 South 35th St.  
3801 East Business SH 31

Evansville, IN 47715  
Mechanicsburg, PA 17050  
Council Bluffs, IA 51501  
Corsicana, TX 75109

812-428-9350  
717-766-2566  
712-322-2294  
903-872-8475

Fax 812-428-9353  
Fax 717-697-2371  
Fax 712-322-6673  
Fax 903-872-7732